



EXECUTIVE OFFICE: NEWARK, NJ 07105
PHONE: 973-589-9150 FAX: 973-589-4432
MIDWEST OFFICE: TOLEDO, OH 43605
PHONE: 419-691-2491 FAX: 419-693-3806
TECHNICAL SERVICE PHONE NO. 800-347-5343

FISKE's Moly EP 00

Typical Tests

Type of Thickener	Lithium
Worked Penetration	390 – 420
NLGI No.	00
Dropping Point	335°F
Mineral Oil Viscosity @ 100°F	300 SUS
@ 210°F	49 SUS
Pour Point of Mineral Oil	-30°F
Flash Point of Mineral Oil	350°F
Timken OK Load	45 lbs.
Color	Steel Grey
Character	Smooth
Contains Technical Fine Molybdenum Disulfide	